



## TECHNICAL DATA SHEET

### RENOLIT ALKORPLAN3010 – Type 35315

#### Application:

Printed, homogenous sheet for the waterproofing of swimming pools with increased protection against staining and abrasion.

**TECHNICAL DATA SHEET** according to the European standard EN 15836, Plastics — Plasticized poly vinyl chloride (PVC-P) membranes for in ground swimming pools — Part 1: Homogenous membranes of nominal thickness equal to or greater than 0,75 mm.

Characteristic	Value	Test Method
<b>Composition specifications</b>		
Mass per unit area	1,27 ± 0,02 kg/m <sup>2</sup>	EN 1183-1
Water absorption	≤ 1 % masse	EN ISO 62 Method 1
CaCO <sub>3</sub> content	≤ 3 % masse	Atomic absorption spectrometry
<b>Dimensional specifications</b>		
Mean thickness	0,75 mm ± 3%	EN 1849-2
<b>Mechanical specifications</b>		
Tensile strength	≥ 17 N/mm <sup>2</sup>	EN 12311-2 A
Elongation at break	≥ 300 %	EN 12311-2 A
Tear resistance	≥ 70 N/mm	EN 12310-2
Dimensional stability	≤ 3 %	EN 1107-2
Resistance to foldability at low temperature	≤ -25 °C	EN 495-5
Peel resistance of joints	≥ 1,6 N/mm	EN 12316-2
Shear resistance of joints	≥ 10 N/ mm <sup>2</sup>	EN 12317-2
Watertightness	< 1 x 10 <sup>-3</sup> l/m <sup>2</sup> ·day according EN 16582-1	EN 14150
<b>Durability specifications</b>		
Abrasion resistance	≥ 500 cycles; Rating ≥ 3	EN ISO 5470-1
Resistance to an artificial ageing of 19 GJ/m <sup>2</sup> (6000 h)	≥ 3 according EN 20105-A02	EN ISO 4892-2:2006 Method A cycle n°1
Resistance to action of microorganisms	Mass Loss ≤ 1 %	EN ISO 846:1997 / D
Resistance to streptovercillum reticulum bacteria ATCC 25607	No Stains	EN ISO 846:1997 / C
Chlorine resistance	Rating ≥ 3	EN 15836 Annex C
Resistance to staining agents	Rating ≥ 4	EN 15836 Annex D

The composition of the membrane conforms to European legislation (CMR content cat. 1 and 2 less than 0.1% - Sum of Pb, Cd, Hg, Cr (IV) and As less than 100 mg/kg).

#### Storage Conditions:

The rolls must be stored horizontally in their original packaging in a dry room at a moderate ambient temperature (15 – 25 °C).

February 7, 2017